

BIOREL REINFORCEMENT

*REINFORCEMENT
Textile with
biodegradable adhesive*

PRODUCT DESCRIPTION

BIOREL 74G reinforcement has an excellent adhesion on a wide range of substrates. The article is biodegradable.

TECHNICAL DATA

74G 6100 00 CW0	
SUPPORT	COTTON WOVEN (SATIN)
COUNT OF YARN WARP/WEFT	NE 20/12
YARNS/SQCM WARP/WEFT	39x22
THERMOADHESIVE RESIN	ADESIVO BIODEGRADABILE BASE POLIESTERE
TOTAL WEIGHT (gr/smq)	265 +/- 10%

BENEFITS

-  **Biodegradable**
-  **Suitable for a wide range of substrates**

METHOD OF USAGE:

- Temperature of the shape: from 90°C to 150°C depending on the nature of lining and upper used (natural or synthetic).
- Contact time: from 10 to 15 seconds (high operating temperatures allow contact times reduced and vice versa).
- Pressure: 3-5 atm

ATTENTION: do not exposure to direct sunlight and do not store in hot and humid places.